



SPARTACOTE™ SURFACE BUILD 150™

SPARTACOTE™ SURFACE BUILD 150™ is a medium viscosity, 100% solids epoxy coating. This product may also be used as a filler coat on concrete that has been mildly spalled due to excessive wear. SPARTACOTE SURFACE BUILD 150 also provides a high gloss finish. SPARTACOTE SURFACE BUILD 150 can be applied to primed concrete surfaces in manufacturing areas, aisle ways, commercial and institutional facilities.

**Globally Proven
Construction Solutions**



FEATURES/BENEFITS

- Low VOC
- Impact Resistant
- Excellent adhesion to concrete and ferrous metal
- Superior inter-coat adhesion with SPARTACOTE Polyaspartics and Epoxy
- Excellent carbonation resistance
- Excellent Build Coat over existing Tile

SHELF LIFE

Two years unopened. Store at 4° to 24°C in a covered area (out of the sun). Material should be kept in a cool dry place prior to application. Do not allow to freeze.

MANUFACTURER

LATICRETE Australia Pty Ltd
29 Telford Street
Virginia, QLD 4014 Australia

Telephone: 07 3865 1599
Toll Free: 1800 331 012
Fax: 07 3865 2250
Internet: www.laticrete.com.au

PACKAGING

Part A

7.6 L (2 gal) Pail
18.9 L (5 gal) Pail

Part B

3.7 L (1 gal) Pail
18.9 L (5 gal) Pail

APPROXIMATE COVERAGE

Thickness in mm	Sq. Metre Per Coat/Litre (m ² /L)
0.25	3.9
0.5	2.0

COLOUR

Available in Clear. Sand Beige and Light Grey available upon request.

Limitations

- This product is not recommended for exterior applications or immersion service.
- Do not apply this product at ambient or floor temperatures below 13°C or over 32°C or if the relative humidity is above 92%.
- Please note that with all resinous coating systems, exterior full sun environments in warm climates may exhibit above average surface temperatures. This is especially true with darker finishes. As a result, resinous systems may not be ideally suited for exterior pool deck applications

Cautions

FOR PROFESSIONAL USE ONLY

- Thoroughly read all technical data sheets, application guidelines, warranty disclaimers and Safety Data Sheets (SDS) prior to use. Application guides are available at www.laticrete.com.au
- Wear safety eye protection when applying. Contact with eyes may cause irritation. Flush eyes with water for 15 minutes, if symptoms persist seek medical attention.
- Wear safety gloves.
- Until cured, may irritate eyes and skin. Avoid contact with eyes and or prolonged contact with skin. In case of contact, flush thoroughly with water.
- Material should be kept in a cool dry place prior to application
- Product must not freeze.

Mock-ups and field test areas are required in order to validate performance and appearance related characteristics (including but not limited to colour, inherent surface variations, wear, anti-dusting, abrasion resistance, chemical resistance, stain resistance, coefficient of friction, etc.) to ensure system performance as specified for the intended use, and to determine approval of the decorative flooring system.

TECHNICAL DATA

Applicable Standards and Test Methods

ASTM D4060, ASTM C307

Physical & Working Properties

Gloss Units at 16°C	100
% Volume Solids	100%
% Weight Solids	100%
Wet Film Thickness	0.25 - 0.5 mm
Application Surface Temp	13°C to 32°C
Drying Time	12 Hours
Pot Life	25 Minutes
Abrasion Resistance	92 mg max weight loss
Tensile Strength	13.1 MPa (1900 psi)

Specifications are subject to change without notification. Technical data shown in product data sheets are typical but reflect laboratory test procedures conducted in laboratory conditions. Actual field performance and test results will depend on installation methods and site conditions. Field test results will vary due to critical job site factors. All recommendations, statements and technical data contained in this data sheet are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty or guaranty of any kind. Satisfactory results depend upon many factors beyond the control of LATICRETE Australia. User shall rely on their own information and tests to determine suitability of the product for the intended use and user assumes all risk, loss, damage, expense and liability resulting from their direct use, indirect use or consequential to their use of the product. LATICRETE shall not be liable to the buyer or any third party for any injury, loss or damage directly or indirectly resulting from use or inability to use the product.

INSTALLATION

Surface Preparation

Assure substrate to be coated is clean, dry, and in sound condition. All laitance, curing compounds, concrete hardeners, and other surface contaminants must be removed. Shot-blast or acid etch areas to be coated.

Product must not freeze. Combine Part A with Part B, mechanically mix with a power drill at low speed for approximately 2 minutes. No induction time is required prior to use. If micro-media agents are to be incorporated, they are to be added after thoroughly mixing A and B. Material may be thinned with up to 10% xylene

Mixing

11.4 L Kits

Stir contents of Part A 11.4 L Pail. Then add 3.8 L can of Part B activator, mechanically mix for approximately 2 minutes.

18.9 L Pails

Stir contents of Part A 18.9 L pail. Mix by volume, 2 parts Component A to 1 Part Component B activator. Mechanically mix for approximately 2 minutes.

NOTE: Once mixing is complete, immediately pour the entire contents onto the floor. Leaving mixed material in the bucket will generate excessive heat.

Application:

Flat or Notched squeegee application is recommended, with perpendicular back-roll using an 46 cm long 10 mm nap roller to achieve uniform film thickness. Small chip brushes may be used along the perimeter and in more difficult to reach areas.

Clean up with Xylene or Acetone immediately following use.

AVAILABILITY AND COST

Availability

LATICRETE® and SPARTACOTE™ materials are available worldwide.

For Distributor information:

Toll Free: 1800 331 012

Telephone: 07 3865 1599

For online distributor information, visit LATICRETE at www.laticrete.com.au

Cost

Contact a LATICRETE Distributor in your area.

MAINTENANCE

The long term performance, appearance, and life expectancy of wear surface products are critically dependence upon a good routine maintenance program designed specifically for the installed wear surface. SPARTACOTE polyaspartic and epoxy floor coating systems are nonporous, causing dirt and contaminants to remain on the surface. The use of properly placed walk-off mats, inside and outside, will help increase the life of the floor. Recommend maintenance program consist on frequent and through cleaning utilizing a neutral pH cleaner (e.g. Simple Green®). Frequency of washing will vary depending on floor usage type, traffic and age.

Please Refer to TDS 1420 "SPARTACOTE Floor Maintenance Guide" available at www.laticrete.com.au for more information.

TECHNICAL SERVICES

Technical assistance

Information is available by calling:

Toll Free: 1800 331 012

Telephone: 07 3865 1599

Fax: 07 3865 2250

Technical and safety literature

To acquire technical and safety literature, please visit our website at **www.laticrete.com.au**

DISCLAIMER

- The information contained in this document is given in good faith and to the best of our knowledge is true and accurate.
- This information is subject to change without notice and it is the responsibility of the user to obtain up to date and current information.
- The use of this product is beyond our control and LATICRETE is not responsible for any loss or damage arising from the incorrect use of this product.

LATICRETE Australia Pty Ltd

29 Telford Street, Virginia

QLD 4014 Australia

1800 331 012

www.laticrete.com.au