



# CLEAR PU WB

DS-896-0721

**Globally Proven  
Construction Solutions**



## 1. PRODUCT NAME

CLEAR PU WB

## 2. MANUFACTURER

LATICRETE Europe S.r.l. a socio unico

Via Paletti, snc, 41051

Castelnuovo Rangone MO, Italy

Telephone: +39 059 535540

Email: [info@laticreteurope.com](mailto:info@laticreteurope.com)

Website: [laticrete.eu](http://laticrete.eu)

## 3. PRODUCT DESCRIPTION

CLEAR PU WB is a clear, water-soluble two-part polyurethane sealer/finish coating that offers above average chemical and abrasion resistance.

With initial surface preparation and priming, it may be applied directly to a variety of substrate including concrete, metal/steel, epoxy, and polyaspartic. CLEAR PU WB provides good impact, abrasion, and chemical resistance characteristics.

CLEAR PU WB is formulated with an aliphatic hardener which gives it good UV stability, making it suitable for both interior and exterior applications. It is available in a low gloss or matte finish. For more information regarding specific systems or to discuss your next project, please contact us today.

### Uses

- As a clear top coat

- Within seamless multi-build LATICRETE® flooring systems including GUARD, BUILD, QUARTZ, FLAKE, FLOW, STAIN, and SEAL
- For interior and exterior use
- Industrial and heavy traffic applications
- Pedestrian areas
- Schools and educational facilities
- Hospitals and healthcare facilities
- Laboratories and clean rooms
- Retail spaces and shopping malls
- Showrooms and museums
- Stadium, sports, and event spaces
- Parking garages

### Advantages

- Safe, water-based formula
- Good weatherability and UV resistance, even outdoors
- Superior adhesion to various substrates — can bond to metal/steel
- Hygienic and easy to clean — good resistance to detergents and solvents
- Good chemical, abrasion, impact and wear resistance — ideal for high traffic and industrial applications
- Long working time — 2 hours
- Available in low gloss (<37 GU) or matte (<17 GU)

### Suitable Substrates

- Steel
- Metal
- Wood
- Concrete
- Epoxy Coating
- Polyaspartic Coating

### Packaging

CLEAR PU WB: Low Gloss Finish

- 1,2 kg kit (1 kg Part A + 0,2 kg Part B)
- 6 kg kit (5 kg Part A + 1 kg Part B)
- 12 kg kit (10 kg Part A + 2 kg Part B)

CLEAR PU WB MATTE: Matte Finish

- 1,1 kg kit (1 kg Part A + 0,1 kg Part B)
- 5,5 kg kit (5 kg Part A + 0,5 kg Part B)
- 11 kg kit (10 kg Part A + 1 kg Part B)

### Approximate Coverage / Consumption

- ~10 m<sup>2</sup> per 1 kg of product
- ~100 g per m<sup>2</sup> per coat

Coverage values are approximate and will vary based on surface condition, preparation methods and application technique.

### Shelf Life

Containers are to be kept tightly sealed. Do not freeze. Store above 40°F (4°C). Stir well before using as some settlement will occur during storage. Shelf life is one year in factory-sealed containers when properly stored. 12 months unopened. Store at 40°F to 75°F (4°-24°C) in a covered area (out of the sun). Material should be kept in a cool dry place prior to application.

### Limitations

- Please note that with all resinous coating systems, exterior full sun environments in warm climates may exhibit above average surface temperatures. This is especially true with darker finishes. As a result, resinous systems may not be ideally suited for exterior pool deck applications.
- Ferrous metals such as steel and iron must be pretreated with mechanical abrasion.
- DO NOT apply in the presence of moisture.

### Cautions

Thoroughly read all technical data sheets, application guidelines, warranty disclaimers and Safety Data Sheets (SDS) prior to use.

- Wear protective gloves, protective clothing and eye protection.
- Use tape to protect areas not being treated.
- Surface temperature may be elevated if exposed to direct sunlight in hot climates.
- Keep out of reach of children.

## 4. TECHNICAL DATA



### Physical Properties

Classification according to EN 13813:	SR-B2,0-AR2-IR20	
Reaction to fire according to EN 13501-1:	Bfl-S1	
Basis:	Water based, polyurethane resins	
Appearance:	Low Gloss or Matte	
	<b>Value</b>	<b>Test Method</b>
Bond strength:	> 2,6 N/mm <sup>2</sup>	EN 13892-8
Wear Resistance:	< 150 µm	EN 13892-4
Impact Resistance:	> 20 Nm	EN ISO 6272-1
Temperature Resistance:	From -30°C to +90°C	

### Working Properties

Consistency:	Fluid
Wet Density:	1.05 kg / lt (+/- 0.05)
Application Temperature	From + 10°C to + 35°C
Application R.H.:	< 70%
Mix Ratio (A:B):	10:1 by weight
% Solids:	32% (+/- 2%)
Working Time:	3 hours
Dust-free:	30 - 40 minutes
Dry to Touch:	~3 hours
Minimum Re-Coat Time:	6 hours
Maximum Re-Coat Time:	24 hours
Maximum/Thickness:	40 - 100 microns
Foot Traffic:	72 hours
Vehicular Traffic:	7 days
Final Cure:	7 days

(at 20°C, 60% R.H.)

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

## 5. INSTALLATION

### Surface Preparation - Concrete

Surfaces to be coated must be free of grease and any other contaminants that may impede adhesion. Always check the surface for any bond inhibitors prior to application. Any repairs must be addressed prior to application and should be repaired in accordance with ICRI standards. Do not use alcohol to clean prior to application.

Concrete must be mechanically profiled. Ensure that all surface laitance is removed prior to coating. If wet grinding, allow surface to fully dry prior to coating. Properly prepared concrete substrate must have a tensile strength  $\geq 1,4$  MPa when tested in accordance with ASTM C1583.

Concrete must be tested for relative humidity (RH) prior to installation of any coatings. The RH of the slab must not exceed 3%.

### Surface Preparation - Over Existing Tile

Existing tile must be mechanically abraded and profiled using a floor grinder, shot blaster, or other similar equipment. Refer to TDS 450: Installation Guideline for Installing LATICRETE® Floor Coatings over Existing Tiled Surfaces.

## Surface Preparation - Metal/Steel

Surfaces to be coated must be free of grease, oils, cutting fluids and any other contaminants that may impede adhesion. Always check the surface for any bond inhibitors and clean the surface prior to application.

## Mixing Part A with Part B

Mix Part A and Part B 10:1 by weight (Part A : Part B), using a clean, dry working vessel. Use a paddle mixer on slow speed for 2 minutes. Avoid overmixing or creating a vortex that could introduce air. Do not mix below the dew point, which will shorten the pot life. No induction or waiting time is required prior to use.

## Application

CLEAR PU WB can be applied by brush, roller or sprayer in two coats. It can also be applied with a plastic spatula or squeegee, which may only require one coat. Spread evenly over all prepared surfaces to desired thickness, in a total thickness between 40 and 100 µm. Use a brush or small roller around penetrations, columns, and any other obstructions. Periodically check mil thickness using a wet film thickness (WFT) gauge. Do not allow the product to puddle or pool. Contact LATICRETE directly for specifics on effective application techniques

The applied material will be dry to the touch after about 3 hours from application, dependent on ambient temperature, substrate temperature and humidity. Product may be re-coated within 6 to 24 hours following application. Light foot traffic is acceptable about 72 hours following application and vehicular traffic is acceptable 7 days after application.

## Notes

Mock-ups and field test areas are required in order to validate performance and appearance relate characteristics (including but not limited to color, inherent surface variations, wear, anti dusting, abrasion resistance, chemical resistance, stain resistance, coefficient of friction, etc.) to ensure system performance as specified for the intended use, and to determine approval of the coating system.

Variability in job site conditions (including but not limited to surface preparation, sunlight, humidity, dew point, temperature, etc.) during application of LATICRETE flooring products may lead to fisheyes, blistering, pinholes, wrinkling, or outgassing of air in the concrete and are not product defects. Additional coats, shading or evening application may be required.

## 6. AVAILABILITY AND COST

### Availability

LATICRETE® materials are available worldwide. For distributor information, please contact LATICRETE Europe S.r.l. a socio unico:  
+39 059 535540  
[info@laticreteurope.com](mailto:info@laticreteurope.com)

For on-line distributor information, visit [www.laticrete.eu](http://www.laticrete.eu).

### Cost

Contact LATICRETE Europe S.r.l. a socio unico to obtain complete information and cost.

## 7. WARRANTY

The supplier warrants that the product will not deteriorate under normal conditions and use. The warranty validity of one (1) year. Contact Technical Services for further information. See 10. FILING SYSTEM:

- DS 230.13EU: 1 Year Product Warranty

## 8. MAINTENANCE

The long term performance, appearance, and life expectancy of wear surface products are critically dependence upon a good routine maintenance program designed specifically for the installed wear surface. LATICRETE® polyaspartic, polyurethane, and epoxy floor coating systems are nonporous, causing dirt and contaminants to remain on the surface. The use of properly placed walk-off mats, inside and outside, will help increase the life of the floor. Recommend maintenance program consist of frequent and thorough cleaning utilizing a neutral pH cleaner. The frequency of washing will vary depending on floor usage type, traffic and age.

## 9. TECHNICAL SERVICES

### Technical Assistance

Information is available by calling or emailing the Technical Service Hotline:  
+39 059 535540  
[technicalservices@laticreteurope.com](mailto:technicalservices@laticreteurope.com)

### Technical and Safety Literature

To obtain technical and safety literature, please visit our website at [www.laticrete.eu](http://www.laticrete.eu).

### Warning

The information and the instructions in the data sheet, although based on knowledge gained through years of applications, are indicative. LATICRETE® is unable to directly control the installation methods and conditions of products and does not assume any liability arising from their implementation. Those who want to use LATICRETE® products should conduct adequate tests to determine the site specifications. Results shown are typical but reflect test procedures used. Actual field

performance will depend on installation method and site conditions.

LATICRETE® products are covered by a warranty within the limits of what is established by our general conditions of sale and within the limits of correspondence related to technical specifications and applicable certifications, as expressly indicated in the product data sheets, documentation, or applicable technical documentation.

## 10. FILING SYSTEM

Additional product information is available on our website at [laticrete.eu](http://laticrete.eu). The following is a list of related documents:

- DS 230.13EU: 1 Year Product Warranty
- DS 560: LATICRETE® Europe MOISTURE VAPOR BARRIER
- TDS 420: LATICRETE® Floor Maintenance Guide
- TDS 450: Installation Guideline for Installing LATICRETE® Floor Coatings over Existing Tiled Surfaces
- DS 3127: Surface Preparation for LATICRETE® Resinous Flooring