



HYDRO BAN® PREFORMED IC

Special IINSIDE corner made from non-woven and a flexible coating.

**Globally Proven
Construction Solutions**



MAIN FEATURES

- Totally waterproof
- Waterproofs against both pressure and negative pressure
- Easy to apply
- UV-resistant
- Deformable even in low temperatures

CERTIFICATION

- DIN EN ISO 9001: 2008

FIELD OF APPLICATION

- Sealing perimetral IINSIDE corners between walls and floor
- Waterproofing expansion and dividing joints with waterproofing membrane as AQUA BARRIER or AQUA BARRIER RDY.

MANUFACTURER

LATICRETE EUROPE S.r.l. – Via Borgogna, 8 – 20122
MILANO - ITALIA
Via Viazza 1° Tronco, 19 – 41043 Formigine (MO) -ITALIA
Telefono +39 059 557680
Website laticrete.eu

Material composition

- Substrate: Two outer layers of polypropylene non-woven - -
 Coating: Thermoplastic elastomere, resistant to ageing

Colours

Olive green (Other colours in accordance to RAL upon request)

Side length: (approx.)

120 mm x 120 mm

Total thickness (approx)

0,90 mm

Material weight (approx.):

14 g / piece

Resistance to temperature: min. / max

- 30°C / + 90°C

Quantities required

Specified in pieces

Storage

Cool and dry, protect against sunlight, use within 24 months after receipt.

TECHNICAL SPECIFICATIONS

Physical Properties: (approx.)	DIN	Value
Burst pressure: max.	Internal	> 1,5 bar
Resistance to water pressure	DIN EN 1928 (Version B)	> 1,5 bar

Chemical Properties:		
Resistance after storage over 7 days by room temperature in following chemicals i		+ = resistant - = not resistant
Hydrochloric acid 3%	Internal method	+
Sulphuric acid 35%	Internal method	+
Citric acid 100g/l	Internal method	+
Lactic acid 5%	Internal method	+
Potassium hydroxide 3% / 20%	Internal method	+ / +
Sodium hypochlorite 0,3g/l	Internal method	+
Acqua salata (20g/l acqua salata marina)	Internal method	+

AVAILABILITY AND COST**Availability**

LATICRETE AND LATAPOXY materials are available worldwide. For distributor information, please contact LATICRETE EUROPE S.r.l. Telephone +39 059 557680. For on-line distributor information, visit www.laticrete.eu

Cost

Contact a LATICRETE and LATAPOXY closer distributor to obtain complete information and cost.

WARRANTY

The supplier warrants that the product will not deteriorate under normal conditions and use. The warranty validity of one (1) year.

Contact Technical Support for further information.

MAINTENANCE

LATICRETE and LATAPOXY are products of high quality designed to achieve lasting installations and avoid maintenance, however performance and durability may depend on properly maintaining products, depending of the cleaning products used.

TECHNICAL SERVICE**Technical assistance**

For information contact: +39 059 557680

info@laticreteeuropa.com

Technical and safety literature

To obtain technical and safety literature, please visit our website at www.laticrete.eu

Warning

The information and the instructions in the data sheet, although based on knowledge gained through years of applications, are indicative. LATICRETE unable to directly control the installation conditions and modalities of application of products, do not assume any liability arising from their implementation. Those who want to use the LATICRETE products must conduct adequate tests to determine the site specifications. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation method and site conditions.