




NXT[®] Level Flow

High Flowing Underlayment

NEW



Data Sheet 36623.0

NXT[®] Level Flow is a cement-based, high flowing, easy-to-use underlayment for use in leveling interior substrates. NXT Level Flow produces a flat, smooth and hard surface for the installation of finished flooring.



FEATURES	BENEFITS
High flowing	Great coverage
Low viscosity	Easy to apply
Self-leveling	Smooths existing rough concrete, provides a flat floor
Pourable and pumpable	From small to larger applications
Can be applied over concrete testing up to RH of 100%	Minimal downtime

Suitable Substrates

- Concrete slabs

Uses

- Commercial, retail (malls & shops)
- Healthcare
- Education (schools & universities)
- Residential
- Hotels

Item

0903-0050-21

Advantages

- High flowing and easy-to-use
- Can be placed from 1/8" to 2" (3 mm to 51 mm)
- Inorganic; will not contribute to mold/mildew growth
- Suitable surface for most finished floor goods as soon as 48 hours
- 4,000 PSI (27.6 MPa) in 28 days
- Walkable in 3 to 4 hours

Packaging

50 lb (22.7 kg) bag, 56 bags per pallet






NXT[®] Level Flow

Contrapiso de alta fluidez

NUEVO



Especificación 36623.0

NXT[®] Level Flow es un contrapiso de alto flujo y fácil de usar, formulado a base de cemento para usar en la nivelación de sustratos interiores. El nivelador NXT Level Flow crea una superficie plana, lisa y dura para la instalación de acabados de piso.



CARACTERÍSTICAS	BENEFICIOS
De alta fluidez	Gran cobertura
Baja viscosidad	Fácil de aplicar
Autonivelante	Alisa el hormigón en bruto existente, proporciona un piso plano
Apto para vertido y bombeo	De aplicaciones pequeñas a grandes
Puede ser aplicado sobre concretos con una humedad relativa máxima de 100%	Tiempo de inactividad mínimo

Sustratos adecuados

- Pisos de hormigón

Usos

- Comercial, minorista (centros comerciales y tiendas)
- Atención médica
- Educación (escuelas y universidades)
- Uso residencial
- Hoteles

Ventajas

- De alta fluidez y fácil de usar
- Se puede colocar de 1/8" a 2" (3 mm a 51 mm)
- Inorgánico: no contribuye a la formación de moho y hongos
- Superficie apta para la mayoría de los acabados de piso después de 48 horas
- 27.6 MPa (4,000 PSI) en 28 días
- Se puede pisar entre tres a cuatro horas

Artículo N.º

0903-0050-21

Presentación

Bolsa de 22.7 kg (50 lb) bag, 56 bolsas por palet

