



NXT® Skim

DS-506.0-0519

**Globally Proven
Construction Solutions**



1. PRODUCT NAME

NXT® Skim

2. MANUFACTURER

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 1235
Toll Free: 1.800.243.4788, ext. 1235
Fax: +1.203.393.1684
Website: laticrete.com

3. PRODUCT DESCRIPTION

NXT Skim is a premium quality, fast-drying, cement-based underlayment designed for skim-coating, smoothing and leveling prior to the application of floor coverings. Apply from skim depth to 1" (25 mm). Install finished flooring as soon as 20 minutes after application. This trowel-applied product has a superior creamy consistency making it the ideal choice for skim coat applications.

Uses

- Repairs

Advantages

- Apply from skim depth to 1" (25 mm)
- Rapid setting formula
- Ready for finished flooring in as soon as 20 minutes
- Direct replacement for DRYTEK Skimcoat

Suitable Substrates

- Concrete
- Vinyl Tile
- Cement Terrazzo
- Exterior Glue Plywood

- Ceramic Tile and Stone
- Cement Mortar Bed
- Non-cushioned sheet vinyl (Requires NXT Embossing Admix)
- Cement Backer Board

Packaging

4X10 LBS. (4X4.5KG) BAG / 44 per pallet /
Part: 0902-0410-21

Approximate Coverage

Up to 300 ft² (27.9 m²) at Skim Depth

Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for one (1) year if stored off the ground in a dry area.

Limitations

- For interior use only.
- Do not install NXT Skim over particleboard, chipboard, hardboard (Masonite®), Luan panels, asbestos, gypsum-based patching materials, asphalt, coal tar, or lightweight insulating concrete or any other dimensionally unstable materials.
- NXT Skim is not recommended for steel-wheeled traffic.
- Do not install when surface temperature is below 40°F (4°C) or above 90°F (32°C).
- Do not install over painted surfaces.
- Do not exceed recommended mixing ratio as indicated in mixing instructions. Over watering will weaken product properties.
- Do not apply NXT Skim over waterproofing or crack isolation membranes.
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane on top of the dry NXT Skim.
- Not for use in submerged applications.
- During cold weather, protect finished work from traffic until fully cured.

Cautions

- Read and understand the Product Data Sheet and Safety Data Sheet.
- Check www.laticrete.com for any technical bulletins or updated information about the product and its application.
- Contact your local LATICRETE Technical Sales Representative with any questions.
- Consult SDS for more safety information.
- Contains portland cement. Causes skin irritation and serious eye damage. May cause an allergic skin reaction. Wear

protective clothing, gloves and eye protection. In case of contact, flush thoroughly with water.

- Do not take internally.
- Keep out of reach of children.

4. TECHNICAL DATA



Physical Properties

Test	Test Method
Application Depth	Skim depth to 1" (25 mm)
Walkable	15 – 20 minutes at 70°F (21°C)
Set Time (ASTM C1708)	Initial @ 10 - 15 min. Final @ 15 - 20 min.

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

5. INSTALLATION

Surface Preparation

- Clean substrate to eliminate dust, dirt, oil, grease, paint or any contaminants which may inhibit bonding. Do not use chemicals to clean substrate. Remove any loose particles and vacuum.
- Test surface bond strength of substrate. If minimum 72 psi (0.5 MPa) bond strength is not achieved or the substrate is contaminated, remove contaminants by mechanical means. Retest surface.
- Inspect for contraction joints, construction joints, and cracks in the substrate which may be subject to movement after installation of NXT® Skim. These must be maintained as joints in the new surface.
- Maintain substrate temperature between 40°F (4°C) and 90°F (32°C) during application and air temperature between 50–90°F (10–32°C) during drying. Provide adequate ventilation to ensure uniform drying.
- For very absorptive concrete, apply a fine mist of water on top of the prepared concrete using a pump garden type sprayer, just prior to NXT SKIM application. Concrete should readily absorb water. Broom out excess standing water. Do not apply NXT SKIM where there is standing water on top of the concrete. If water beads or does not absorb within 60 seconds, additional surface prep is needed.

Embossing Non-Cushioned Vinyl Floors and VCT

Completely remove any wax or other coatings. Roughen smooth surfaces. Wash and rinse thoroughly with clean water. Allow to dry.

Preparing Ceramic Tile or Terrazzo

Ensure tiles are well bonded to the substrate. Mechanically abrade with a carborundum disk. Wash and rinse thoroughly with clean water. Allow to dry.

Preparing Non-Water Soluble Cutback Adhesive

Scrape non-water soluble cutback adhesive residue from the floor and remove excess material. Ensure remaining adhesive residue is completely dry.

Mixing

Mix 2.5 qts. (2.4 L) to 3.0 qts (2.8 L) of clean cool water per 10 lb. (4.5 kg) bag of NXT SKIM. Add product to water and mix for 2-3 minutes with a heavy duty drill (650 rpm) to obtain a lump free mix. Note: material can be re-mixed to extend pot-life but do NOT add more water when re-mixing.

Mixing with NXT EMBOSSING ADMIX (for embossing non-cushioned vinyl and VCT flooring)

Mix 3.5 qts. (3.1 L) of NXT EMBOSSING ADMIX per 10 lb. (4.5 kg) bag of NXT SKIM. Add NXT SKIM to NXT EMBOSSING ADMIX and mix for 2-3 minutes with a heavy duty drill (650 rpm) to obtain a lumpfree mix. Note: material can be re-mixed to extend pot-life but do NOT add more admix or water when re-mixing.

Application

Apply blended material to substrate with trowel at a thickness from feather-edge to 1" (25 mm) for all surfaces. After initial set of material (approx. 10–15 min.), remove all overlap marks, seams and inconsistencies by scraping with a steel trowel. Key in but do not over trowel. Material can be walked on after 15–20 minutes at 70°F (21°C) or higher, depending on thickness.

Flooring Installation

Finished floor goods may be installed as soon as 20 minutes after application, subject to thickness, drying conditions and type of flooring materials. Always refer to finished floor manufacturer's recommendations regarding installation instructions, restrictions, moisture conditions and compatibility. Always test performance suitability and compatibility of finished floor systems prior to their application. Sample surfaces should be installed as a field test so as to be representative of entire surface and tested for intended use.

6. AVAILABILITY AND COST

Availability

LATICRETE materials are available worldwide.

For Distributor Information, Call:

Toll Free: 1.800.243.4788

Telephone: +1.203.393.0010

For on-line distributor information, visit LATICRETE at laticrete.com

Cost

Contact a LATICRETE Distributor in your area.

7. WARRANTY

See 10. FILING SYSTEM:

- LATICRETE Product Warranty

8. MAINTENANCE

Non-finish LATICRETE and LATAPOXY installation materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

9. TECHNICAL SERVICES

Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 1235
Telephone: +1.203.393.0010, ext. 1235
Fax: +1.203.393.1948

Technical and Safety Literature

To acquire technical and safety literature, please visit our website at laticrete.com.

10. FILING SYSTEM

Additional product information is available on our website at laticrete.com. The following is a list of related documents:

- DS 230.13: LATICRETE® 1 Year Product Warranty (United States and Canada)
- DS 236.0 9235 Waterproofing Membrane
- DS 503.0: NXT® Embossing Admix
- DS 663.0: HYDRO BAN®