

L&M CURE R2™

DS-172.2-0417

Globally Proven Construction Solutions



1. PRODUCT NAME

L&M CURE R2™

2. MANUFACTURER

LATICRETE International, Inc. 1 LATICRETE Park North Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 235
Toll Free: 1.800.243.4788, ext. 235
Fax: +1.203.393.1684
Website: www.laticrete.com

3. PRODUCT DESCRIPTION

L&M CURE R2 is a water based, resin, liquid membrane forming curing compound for freshly finished concrete. Its white pigment reflects the sun's rays to help keep the concrete surface cooler, and maximize water retention. This sprayable liquid maintains efficient water retention performance to comply with ASTM, AASHTO, and most State DOT requirements.

Uses

L&M Cure R2 is best used when maximum curing and sunlight reflectance are required, such as state highways, DOT's, city and country roads, bridge decks, dams and curb and gutter work.

Specification Description

03 39.13: Acrylic Curing Compound: Minimum 25% acrylic solids shall conform to ASTM C309, Type I, and ASTM C1315, Type 1.

Advantages

- White pigmented to protect against moisture loss from sunlight
- Applies easily with conventional spray equipment
- Low odor
- Fast drying
- Dries to white colored resin membrane curing compound.
- Provide excellent early curing properties
- Improves the compressive strength of treated concrete when compared to uncured or improperly cured concrete

Suitable Substrates

Freshly Placed Concrete

Packaging

5 Gal (19 L) 55 Gal (208 L)

Approximate Coverage

Surface porosity determines coverage rate. For best results: Broom finishes - 200 ft²/gal (4.9 m²/L) Steel troweled - 300 ft²/gal (7.3 m²/L)

For rapid dissipation - 400 ft²/gal (9.8 m²/L)

Shelf Life

Containers are to be kept tightly sealed. Do not freeze. Store above 40°F (4°C). Stir well before using as some settlement will occur during storage. Shelf life is one year in factory-sealed containers when properly stored.

Limitations

- Temperature must be over 40°F (4°C) for use
- Apply only to frost free surfaces
- Do not apply over standing water
- Natural dissipation of L&M CURE R2 is dependent upon exposure to direct sunlight and abrasion
- Over application or lack of sunlight or abrasion may inhibit natural dissipation and may require professional removal
- L&M CURE R2 will yellow and darken upon exposure to sunlight and then gradually dissipate
- Remove prior to subsequent toppings, tile, coatings, etc

Cautions

- Keep from freezing
- Keep out of reach of children
- Do not spray near sources of ignition
- Wear protective goggles and gloves
- Please refer to Safety Data Sheet (SDS) before using

Mock-ups and field test areas are required in order to validate performance and appearance related characteristics (including but not limited to color, inherent surface variations, wear, anti-dusting, abrasion resistance, chemical resistance, stain resistance, coefficient of friction, etc.) to ensure system performance as specified for the intended use, and to determine approval of the decorative flooring system.

4. TECHNICAL DATA

Applicable Standard

ASTM C 309, Type II, Class B AASHTO M-148, Type II, Class B

Physical and Working Properties

Property	Observed
Color	White
Specific Gravity	1.03
Moisture Loss @ 200 ft²/gal (5m²/L) 3 days kg/m²	0.45 kg/m ²
Reflectance	62+
Dry Time at 73°F (23°C) to touch	2 Hours
Dry Time at 73°F (23°C) Dry	3-4 Hours
VOC	245 g/L

Specifications are subject to change without notification. Technical data shown in product data sheets are typical but reflect laboratory test procedures conducted in laboratory conditions. Actual field performance and test results will depend on installation methods and site conditions. Field test results will vary due to critical job site factors. All recommendations, statements and technical data contained in this data sheet are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not be construed as a warranty or guaranty of any kind. Satisfactory results depend upon many factors beyond the control of LATICRETE International, Inc. User shall rely on their own information and tests to determine suitability of the product for the intended use and user assumes all risk, loss, damage, expense and liability resulting from their direct use, indirect use or consequential to their use of the product. LATICRETE shall not be liable to the buyer or any third party for any injury, loss or damage directly or indirectly resulting from use or inability to use the product.

5. INSTALLATION

Application

Freshly placed concrete - Surface must be finished to specified requirements prior to the application of L&M CURE R2™. Stir well before using to ensure uniform consistency. Do not dilute. Uniformly apply to fresh concrete surfaces after final troweling when surface water has dissipated. Evenly apply to the concrete surfaces by spray or roller at the rate specified. Do not puddle. Provide adequate ventilation when in an enclosed, highly humid, unvented area. Apply after surface bleed water dissipates. Immediately wash off and squeegee excess cure if it has not dried within four hours.

Cleaning

Prior to product drying, clean up equipment using soap and hot water. After the product hardens, soak with xylene* or other available aromatic solvent. Flush clean.

*Caution: Xylene is flammable and hazardous.

6. AVAILABILITY AND COST

Availability

L&M™ and LATICRETE® materials are available worldwide.

For Distributor Information, Call:

Toll Free: 1.800.243.4788 Telephone: +1.203.393.0010

For on-line distributor information, visit LATICRETE at

www.laticrete.com

Cost

Contact a LATICRETE Distributor in your area.

7. SHORT SPEC

033000: Dissipating resin-based curing compound shall conform to ASTM C 309, Type 1, Class B and local air quality regulations. Cure shall begin to chemically break down when exposed to sunlight and abrasion

8. WARRANTY

See 10. FILING SYSTEM:

DS 230.13: LATICRETE Product Warranty

9. MAINTENANCE

Non-finish LATICRETE and LATAPOXY® installation materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

10. TECHNICAL SERVICES

Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 235 Telephone: +1.203.393.0010, ext. 235

Fax: +1.203.393.1948

Technical and Safety Literature

To acquire technical and safety literature, please visit our website at www.laticrete.com.

11. FILING SYSTEM

Additional product information is available on our website at **www.laticrete.com**. The following is a list of related documents:

DS 230.13: LATICRETE Product Warranty

LBA Continuition Clambols
Appoint board of IMPOSE International, Inc.
MODER Immediately, Inc. - One IMPOSE International, Inc.
MODER Immediately, Inc. - One IMPOSE First North, Berlang, CT 06524-3422 854-1,500,243.4765 ++1,203.393.0010 - www.lost.cata.com
G2016 IMPOSE International, Inc. Altrodemotic shown on the intelligible of properties of their supporter aware.