



LATICRETE[®] Rapid-Set Latex Products

TDS 116

4237 RS RAPID LATEX ADDITIVE* WITH 211 POWDER (or 1:1 PC/Sand)

Install Tile at Temperature	Ready for Foot Traffic	Ready for Heavy Traffic
45° F (7° C)	12 hours	14 hours
50° F (10° C)	6 hours	10 hours
60° F (16° C)	5 hours	8 hours
70° F (21° C)	4 hours	6 hours
80° F (27° C)	3 hours	3-1/2 hours
90° F (32° C)	2 hours	2-1/2 hours
Open Time	50 minutes @ 70°F (21°C)	
Pot Life	80 minutes @ 70°F (21°C)	

101 RAPID LATEX ADMIX WITH 317

Install Tile at Temperature	Ready for Foot Traffic	Ready for Heavy Traffic
45° F (7° C)	16 hours	20 hours
50° F (10° C)	12 hours	16 hours
60° F (16° C)	8 hours	12 hours
70° F (21° C)	6 hours	10 hours
80° F (27° C)	5 hours	7 hours
90° F (32° C)	4 hours	6 hours
Open Time	15 minutes @ 70° F (21°C)	
Pot Life	1 hour @ 70°F (21°C)	

* Product available outside of the United States only.

Technical Data Sheets are subject to change without notice. For latest revision, check our website at www.laticrete.com
TDS 116.doc R 15 August 2013



LATICRETE INTERNATIONAL, INC. ▪ 1 LATICRETE Park North ▪ Bethany, CT 06524-3423 USA
800.243.4788 ▪ support@laticrete.com ▪ www.laticrete.com

©2013 LATICRETE INTERNATIONAL, INC. All trademarks shown are the intellectual properties of their respective owners.