



NXT Self-Leveling Underlayment

Troubleshooting Guide

TDS 205

Complaint	Cause(s)	Prevention
Brown skim discoloration on surface	1. Over watering of product	1. Use a high speed mixer (500rpm) and mix thoroughly for one minute for a smooth creamy mix with no clumps. Follow all mixing instructions on bag. Be sure not to add too much water. Mix no more than two bags at a time with potable water.
White powder residue	1. Over watering of product	1. Use a high speed mixer (500rpm) and mix thoroughly for one minute for a smooth creamy mix with no clumps. Follow all mixing instructions on bag. Be sure not to add too much water. Mix no more than two bags at a time with potable water.
Pin Holes	1. Improper use of primer 2. Surface not properly prepared	1. Use NXT™ Primer with every application. Consult product data sheet (502.0) for information on the use and application of the primer. 2. Substrate should be abraded and free of dust, dirt, oil, grease, loose paint, laitance, efflorescence, curing compounds, sealers, water repellents and other materials that prevent bond. Mechanically scarify the concrete surface to remove any contaminants.
Hairline cracks	1. Improper use of primer 2. Surface not properly prepared 3. Over watering of product 4. Improper drying techniques 5. Telegraphing of cracks from substrate movement in substrate	1. Use NXT Primer with every application. Consult product data sheet (502.0) for information on the use and application of the primer. 2. Substrate should be abraded and free of dust, dirt, oil, grease, loose paint, laitance, efflorescence, curing compounds, sealers, water repellents and other materials that prevent bond. Mechanically scarify the concrete surface to remove any contaminants. 3. Use a high speed mixer (500rpm) and mix thoroughly for one minute for a smooth creamy mix with no clumps. Follow all mixing instructions on bag. Be sure not to add too much water. Mix no more than two bags at a time with potable water. Product should be allowed to cure under normal air circulation. Do not allow for additional air circulators to speed up curing process. 4. Surface must be well cured, dimensionally stable, and free of cracks, curing compounds, sealers, laitance or other surface contamination that inhibits bonding. Maximum variation in the slab shall not exceed 1/8" in 10' (3mm in 3m) from the required finished slope or plane elevation.

<p>Does not adhere to substrate</p>	<ol style="list-style-type: none"> 1. Improper use of primer 2. Surface not properly prepared 	<ol style="list-style-type: none"> 1. Use NXT™ Primer with every application. Consult product data sheet (502.0) for information on the use and application of the primer. Do not allow NXT Primer to puddle. 2. Substrate should be abraded and free of dust, dirt, oil, grease, loose paint, laitance, efflorescence, curing compounds, sealers, water repellents and other materials that prevent bond. Mechanically scarify the concrete surface to remove any contaminants. Do not adhere to loose patches of substrate.
--	---	---

Technical Data Sheets are subject to change without notice. For latest revision, check our website at www.laticrete.com
TDS 205.doc R 28 August 2013



LATICRETE INTERNATIONAL, INC. ▪ 1 LATICRETE Park North ▪ Bethany, CT 06524-3423 USA
800.243.4788 ▪ support@laticrete.com ▪ www.laticrete.com

©2013 LATICRETE INTERNATIONAL, INC. All trademarks shown are the intellectual properties of their respective owners.