



# Installing a SPARTACOTE™ Resinous Floor System over a Cement Self-Leveling Underlayment

## TDS 423

The following provides a guideline to the proper installation of SPARTACOTE™ resinous flooring when installing over selected cement self-leveling underlayments (SLU's).

### PARAMETERS:

- Use only [NXT® LEVEL Plus](#), [SUPERCAP® SC500 PLUS](#), and [SUPERCAP SC650 MC](#).
- Interior concrete substrates.
- Residential and light commercial areas that are exposed to pedestrian foot traffic.
- Not intended for industrial applications, vehicular traffic, hard wheel traffic, or areas where point or impact load damage is possible.
- All projects must be approved by LATICRETE Technical Service Department 1.800.243.4788 x1235.

### PRIMER & SELF LEVELING INSTALLATION:

Prime using [SPARTACOTE Moisture Vapor Barrier](#), [NXT Vapor Reduction Coating](#), or [SUPERCAP Moisture Vapor Control](#) with full sand broadcast over properly prepared concrete substrates. For NXT products follow guidelines in [TDS 230N](#) and the [product data sheet](#). For SUPERCAP products follow guidelines in [TDS 230S](#) and the [product data sheet](#).

Install [NXT LEVEL Plus](#), [SUPERCAP SC500 PLUS](#), or [SUPERCAP SC650 MC](#) per normal instructions. Allow SLU to cure and dry for a minimum of 7 days then conduct a plastic sheet test as per method ASTM D4263. If plastic sheet test shows moisture is present, more drying time is needed.

Once no sign of moisture exists in the SLU, diamond grind the SLU surface to an ICRI CSP of 2-3. Sweep and vacuum thoroughly to remove all dust and debris. Next install a primer coat using [SPARTACOTE Moisture Vapor Barrier](#), [NXT Vapor Reduction Coating](#), or [SUPERCAP Moisture Vapor Control](#) at a thickness of 16 mils (0.4mm). The primer should be allowed to dry for a minimum of 12 hours at 50-90°F (10-32°C).

Install SPARTACOTE resinous floor system per the applicable [System Application Guide](#).

Technical Data Sheets are subject to change without notice. For latest revision, check our website at <https://laticrete.com>  
TDS 423.doc R 13 February 2020



**LATICRETE INTERNATIONAL, INC.** ▪ 1 LATICRETE Park North ▪ Bethany, CT 06524-3423 USA  
800.243.4788 ▪ [support@laticrete.com](mailto:support@laticrete.com) ▪ [www.laticrete.com](http://www.laticrete.com)

©2013 LATICRETE INTERNATIONAL, INC. All trademarks shown are the intellectual properties of their respective owners.